



Material - ASME SA-352 LCB

Standard Specification for Castings for Valves, Flanges, Fittings and Other Pressure Containing Parts

Group - Ferrous Mild Steel Alloys

Sub Group - ASME SA-352 LCB Castings for Valves, Flanges, Fittings and Other Pressure Containing Parts

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.300 max.	Normalising + Tempering or Hardening + Tempering	
Silicon	Si %	0.600 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.045 max.		
Chromium	Cr %	0.500 max.		
Nickel	Ni %	0.500 max.		
Molybdenum	Mo %	0.200 max.		
Vanadium	V %	0.030 max.		
Copper	Cu %	0.300 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
J03003	UNS	USA	Casting
1.1156	DIN	Germany	Casting
1.1156	EN	USA	Casting
GC24E	EN	European Union	Casting
A352 LCB	ASTM	USA	Casting
1.0619	DIN	Germany	Casting
1.0619	EN	European Union	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.