GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASME SA-372 Grade H Class 70

Standard Specification for Carbon and Alloy Steel Forgings for Thin-Walled Pressure Vessels

Group - Ferrous Mild Steel Alloys
Sub Group - ASME SA-372 Grade H Class 70 Carbon and Alloy Steel Forgings for Thin-Walled Pressure Vessels
Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries
Grade Belongs to the Industry - Forgings

Chemical Composition		
Carbon	C %	0.300 - 0.400
Manganese	Mn %	0.750 - 1.050
Phosphorus	P %	0.015 max.
Sulphur	S %	0.010 max.
Silicon	Si %	0.150 - 0.350
Chromium	Cr %	0.400 - 0.650
Molybdenum	Mo %	0.150 - 0.250
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Normalising or Normalising & Tempering or Quenching & Tempering

Mechanical Properties	
Tensile Strength in Mpa	825 - 1000
Yield Strength in Mpa	485 min.
Elongation in %	18 min.
Reduction of Area in %	-
Hardness in BHN	248 min.
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
K13547	UNS	USA	Steel
J 412 5630	SAE	USA	Steel
8635	AISI	USA	Steel
SA-372 Type V Grade 4	ASME	USA	Steel
A 372 Grade H Class 55	ASTM	USA	Steel and Forging
A 372 Grade H Class 65	ASTM	USA	Steel and Forging
A 372 Grade H Class 70	ASTM	USA	Steel and Forging

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.