GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASME SA-376 Grade TP321

Standard Specification for Seamless Austenitic Steel Pipe For High-Temperature Central-Station Service

Group - Ferrous Stainless Steel Alloys

Sub Group - ASME SA-376 Grade TP321 Seamless Austenitic Steel Pipe For High-Temperature Central-Station Service

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Steel and Pipe

Chemical Composition		
Carbon	C %	0.080 max.
Manganese	Mn %	2.000 max.
Phosphorus	P %	0.045 max.
Sulphur	S %	0.030 max.
Silicon	Si %	0.750 max.
Nickel	Ni %	9.000 - 13.000
Chromium	Cr %	17.000 - 19.000
Titanium	Ti %	0.005 - 0.700
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	515 min.
Yield Strength in Mpa	205 min.
Elongation in %	35 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
S32100	UNS	USA	Steel
D 3698 STS 321	KS	Korea	Plate, Sheet and Strip
D 3576 STS 321HTP	KS	Korea	Steel and Pipe
G 4312 SUS 321	JIS	Japan	Plate, Sheet and Strip
G 3463 SUS 321 HTB	JIS	Japan	Steel and Tubing
A 249 TP321	ASTM	USA	Steel and Tubing
SA-813 TP321	ASTME	USA	Steel and Pipe

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.