GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASME SA-403 WP20CB

Standard Specification for Wrought Austenitic Stainless Steel Piping Fittings

Group - Ferrous Stainless Steel Alloys

Sub Group - ASME SA-403 WP20CB Wrought Austenitic Stainless Steel Piping Fittings

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Steel and Pipe

Chemical Composition		
Carbon	C %	0.070 max.
Manganese	Mn %	2.000 max.
Phosphorus	P %	0.045 max.
Sulphur	S %	0.035 max.
Silicon	Si %	1.000 max.
Nickel	Ni %	32.000 - 38.000
Chromium	Cr %	19.000 - 21.000
Molybdenum	Mo %	2.000 - 3.000
Copper	Cu %	3.000 - 4.000
Niobium	Nb %	0.008 - 1.000
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	550 min.
Yield Strength in Mpa	240 min.
Elongation in %	-
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
N08020	UNS	USA	Steel
SA-182 F 20	ASME	USA	Steel and Pipe
SA-240 N08020	ASME	USA	Plate, Sheet and Strip
A 240 N08020	ASTM	USA	Plate, Sheet and Strip
A 182 F 20	ASTM	USA	Forging and Pipe
A358 N08020	ASTM	USA	Steel and Pipe
A 959 N08020	ASTM	USA	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.