GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

# Material - ASME SA-403 WP316N

## Standard Specification for Wrought Austenitic Stainless Steel Piping Fittings

**Group - Ferrous Stainless Steel Alloys**

**Sub Group - ASME SA-403 WP316N Wrought Austenitic Stainless Steel Piping Fittings**

**Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries**

**Grade Belongs to the Industry - Steel and Pipe**

| Chemical Composition | | |
|---|---|---|
| Carbon | C % | 0.080 max. |
| Manganese | Mn % | 2.000 max. |
| Phosphorus | P % | 0.045 max. |
| Sulphur | S % | 0.030 max. |
| Silicon | Si % | 1.000 max. |
| Nickel | Ni % | 10.000 - 13.000 |
| Chromium | Cr % | 16.000 - 18.000 |
| Molybdenum | Mo % | 2.000 - 3.000 |
| Nitrogen | N % | 0.100 - 0.160 |
| Iron | Fe % | Balance |
| - | - | - |
| - | - | - |
| - | - | - |
| - | - | - |
| - | - | - |

| Heat Treatment |
|---|
| Solution Annealing |

| Mechanical Properties | |
|---|---|
| Tensile Strength in Mpa | 550 min. |
| Yield Strength in Mpa | 240 min. |
| Elongation in % | - |
| Reduction of Area in % | - |
| Hardness in BHN | - |
| Impact in Joule | - |

www.gravitycastindia.com

| Cross Reference Table | | | |
|---|---|---|---|
| **Material** | **Standard** | **Country** | **Grade Belong to the Industry** |
| S31651 | UNS | USA | Steel |
| AMS-QQ-S-763 316 | SAE | USA | Steel, Bar, Wire, Shape and Forging |
| D 3698 STS 316N | KS | Korea | Plate, Sheet and Strip |
| NF 49-244 X3CrNiMo17-11-2 | AFNOR NF | France | Steel and Tubing |
| SA-276 S31654 | ASME | USA | Steel, Bar and Shapes |
| A 276 S31654 | ASTM | USA | Steel, Bar and Shapes |
| A 959 Type 316LN | ASTM | USA | Steel |

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.