GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASME SA-479 Type 317

Standard Specification for Stainless Steel Bars and Shapes for Use in Boilers and Other Pressure Vessels

Group - Ferrous Stainless Steel Alloys

Sub Group - ASME SA-479 Type 317 Stainless Steel Bars and Shapes for Use in Boilers and Other Pressure Vessels

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries
Grade Belongs to the Industry - Bars and Shapes

Chemical Composition		
Carbon	C %	0.080 max.
Manganese	Mn %	2.000 max.
Phosphorus	P %	0.045 max.
Sulphur	S %	0.030 max.
Silicon	Si %	1.000 max.
Chromium	Cr %	18.000 - 20.000
Nickel	Ni %	11.000 - 15.000
Molybdenum	Mo %	3.000 - 4.000
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Annealing

Mechanical Properties	
Tensile Strength in Mpa	515 min.
Yield Strength in Mpa	205 min.
Elongation in %	30 min.
Reduction of Area in %	40 min.
Hardness in BHN	-
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
S31700	UNS	USA	Steel
D 3698 STS 317	KS	Korea	Plate, Sheet and Strip
D 3698 STS 317L	KS	Korea	Plate, Sheet and Strip
G 4312 SUS 317	JIS	Japan	Plate and Sheets
G 4311 SUS 317	JIS	Japan	Steel and Bars
SA-813 TP317	ASME	USA	Steel and Pipe
A 182 F 317	ASTM	USA	Steel and Pipe

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.