GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASME SA-479 Type 800

Standard Specification for Stainless Steel Bars and Shapes for Use in Boilers and Other Pressure Vessels

Group - Ferrous Stainless Steel Alloys

Sub Group - ASME SA-479 Type 800 Stainless Steel Bars and Shapes for Use in Boilers and Other Pressure Vessels

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries
Grade Belongs to the Industry - Bars and Shapes

Chemical Composition		
Carbon	C %	0.100 max.
Manganese	Mn %	1.500 max.
Phosphorus	P %	0.045 max.
Sulphur	S %	0.015 max.
Silicon	Si %	1.000 max.
Chromium	Cr %	19.000 - 23.000
Nickel	Ni %	30.000 - 35.000
Copper	Cu %	0.750 max.
Aluminium	Al %	0.150 - 0.600
Titanium	Ti %	0.150 - 0.600
Iron	Fe %	39.500 min.
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Annealing

Mechanical Properties	
Tensile Strength in Mpa	515 min.
Yield Strength in Mpa	205 min.
Elongation in %	30 min.
Reduction of Area in %	-
Hardness in BHN	192 max.
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
A 240 N08800	ASTM	USA	Plate, Sheet and Strip
A 240 N08810	ASTM	USA	Plate, Sheet and Strip
A 358 N08800	ASTM	USA	Steel
A 358 N08810	ASTM	USA	Steel and Pipe
A 959 Type 800	ASTM	USA	Steel
A 959 Type 800H	ASTM	USA	Steel
G 4902 NCF 800	JIS	Japan	Sheets and Plates

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.