



Material - ASME SA-487 Grade 10B

Standard Specification for Low Alloy Steel and Martensitic Stainless Steel Castings Suitable for Pressure Containing Parts

Group - Ferrous Mild Steel Alloys

Sub Group - ASME SA-487 Grade 10B Low Alloy Steel and Martensitic Stainless Steel Castings Suitable for Pressure Containing Parts

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.300 max.	Annealing or Normalising or Hardening + Tempering	
Silicon	Si %	0.800 max.		
Manganese	Mn %	0.600 - 1.000		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.045 max.		
Chromium	Cr %	0.550 - 0.900		
Nickel	Ni %	1.400 - 2.000		
Molybdenum	Mo %	0.200 - 0.400		
Vanadium	V %	0.030 max.		
Tungsten	W %	0.100 max.		
Copper	Cu %	0.500 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	860 min.
			Yield Strength in Mpa	690 min.
			Elongation in %	15 min.
			Reduction of Area in %	35 min.
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SA-487 Grade 10A	ASME	USA	Casting
J23015	UNS	USA	Casting
A487 10B	ASTM	USA	Casting
A732 9Q	ASTM	USA	Casting
J23055	UNS	USA	Casting
4330	AISI	USA	Forging, Bar, Wire, and Shape
A487 10A	ASTM	USA	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.