GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASME SA-487 Grade 9 Class E (9Q)

Standard Specification for Steel Castings Suitable for Pressure Service

Group - Ferrous Mild Steel Alloys

Sub Group - ASME SA-487 Grade 9 Class E (9Q) Steel Castings Suitable for Pressure Service

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Castings

Chemical Composition		
Carbon	C %	0.050 - 0.330
Manganese	Mn %	0.600 - 1.000
Phosphorus	P %	0.040 max.
Sulphur	S %	0.045 max.
Silicon	Si %	0.800 max.
Vanadium	V %	0.030 max.
Molybdenum	Mo %	0.150 - 0.300
Copper	Cu %	0.500 max.
Chromium	Cr %	0.750 - 1.100
Tungsten	W %	0.100 max.
Nickel	Ni %	0.500 max.
Other	Ot %	1.000 max.
Iron	Fe %	Balance
-	-	-
-	-	-

Heat Treatment
Quenching & Tempering

Mechanical Properties	
Tensile Strength in Mpa	795 min.
Yield Strength in Mpa	655 min.
Elongation in %	15 min.
Reduction of Area in %	35 min.
Hardness in HRC	-
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
J13345	UNS	USA	Steel and Castings
4543 20ChGR	GOST	Russia	Steel
SA-487 Grade 9A	ASME	USA	Steel and Castings
SA-487 Grade 9B	ASME	USA	Steel and Castings
SA-487 Grade 9C	ASME	USA	Steel and Castings
SA-487 Grade 9D	ASME	USA	Steel and Castings
A 487 Grade 9	ASTM	USA	Steel and Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.