

Material - ASME SA-487 Grade CA 15M Class A

Standard Specification for Low Alloy Steel and Martensitic Stainless Steel Castings Suitable for Pressure Containing Parts

Group - Ferrous Stainless Steel Alloys

Sub Group - ASME SA-487 Grade CA 15M Class A Low Alloy Steel and Martensitic Stainless Steel Castings Suitable for Pressure Containing Parts

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Casting

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|-----------------|------------------------------------|-----------|
| Carbon | C % | 0.150 max. | | |
| Silicon | Si % | 0.650 max. | | |
| Manganese | Mn % | 1.000 max. | | |
| Phosphorus | P % | 0.040 max. | Annealing or Hardening + Tempering | |
| Sulphur | S % | 0.040 max. | | |
| Chromium | Cr % | 11.500 - 14.000 | | |
| Nickel | Ni % | 1.000 max. | | |
| Molybdenum | Mo % | 0.150 - 1.000 | | _ |
| Vanadium | V % | 0.050 max. | Mechanical Properties | |
| Tungsten | W % | 0.100 max. | Tensile Strength in Mpa | 620 - 795 |
| Copper | Cu % | 0.500 | Yield Strength in Mpa | 450 min. |
| Iron | Fe % | Balance | Elongation in % | 18 min. |
| - | - | - | Reduction of Area in % | - |
| - | - | - | Hardness in BHN | - |
| - | - | - | Impac <mark>t in Joule</mark> | - |

| Cross Reference Table | | | | |
|-----------------------|----------|---------|-------------------------------|--|
| Material | Standard | Country | Grade Belong to the Industry | |
| SA-487 Grade CA 15M | ASME | USA | Casting | |
| J91151 | UNS | USA | Casting | |
| 410 | SAE | USA | Bar, Wire, Shapes and Forging | |
| A 487 CA 15M | ASTM | USA | Casting | |
| A217 CA 15 | ASTM | USA | Casting | |
| A487 CA 15 | ASTM | USA | Casting | |
| A743 CA 15M | ASTM | USA | Casting | |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.