

Material - ASME SA-487 Grade CA6NM Class A

Standard Specification for Low Alloy Steel and Martensitic Stainless Steel Castings Suitable for Pressure Containing Parts

Group - Ferrous Stainless Steel Alloys

Sub Group - ASME SA-487 Grade CA6NM Class A Low Alloy Steel and Martensitic Stainless Steel Castings Suitable for Pressure Containing Parts

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.060 max.		
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.040 max.	Heating + Reheating + Aging	
Sulphur	S %	0.030 max.		
Chromium	Cr %	11.500 - 14.000		
Nickel	Ni %	3.500 - 4.500		
Molybdenum	Mo %	0.400 - 1.000		
Vanadium	V %	0.050 max.	Mechanical Properties	
Tungsten	W %	0.100 max.	Tensile Strength in Mpa	760 - 930
Copper	Cu %	0.500 max.	Yield Strength in Mpa	550 min.
Iron	Fe %	Balance	Elongation in %	15 min.
-	-	-	Reduction of Area in %	35 min.
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
ASME SA-352 CA6NM	ASME	USA	Casting		
ASME SA-487 CA6NMb	ASME	USA	Casting		
ASME SA-487 Class CA6NM	ASME	USA	Casting		
A 352 CA6NM	ASTM	USA	Casting		
A 356 CA6NM	ASTM	USA	Casting		
A 487 CA6NM	ASTM	USA	Casting		
A743 CA6NM	ASTM	USA	Casting		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.