GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASME SA-508 Grade 22 Class 3

Standard Specification for Quenched and Tempered Vacuum-Treated Carbon and Alloy Steel Forgings for Pressure Vessels

Group - Ferrous Mild Steel Alloys

Sub Group - ASME SA-508 Grade 22 Class 3 Quenched and Tempered Vacuum-Treated Carbon and Alloy Steel Forgings for Pressure Vessels

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Forging

Chemical Composition		
Carbon	C %	0.110 - 0.150
Manganese	Mn %	0.300 - 0.600
Phosphorus	P %	0.015 max.
Sulphur	S %	0.015 max.
Silicon	Si %	0.350 max.
Nickel	Ni %	0.250 max.
Chromium	Cr %	2.000 - 2.500
Molybdenum	Mo %	0.900 - 1.100
Vanadium	V %	0.020 max.
Niobium	Nb %	0.010 max.
Copper	Cu %	0.250 max.
Calcium	Ca %	0.015 max.
Boron	B %	0.003 max.
Titanium	Ti %	0.015 max.
Aluminium	Al %	0.025 max.

Chemical Composition		
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
Heat Treatment		
Annealing or Quenching & Tempering		
Mechanical Properties		
Tensile Strength in Mpa	585 - 760	
Yield Strength in Mpa	380 min.	
Elongation in %	18 min.	
Reduction of Area in %	45 min.	
Hardness in HB	-	
Impact in Joule	54 @ -18°C	

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
K21390	UNS	USA	Steel
A 541 Grade 22 Class 3	ASTM	USA	Steel and Forging
A 541 Grade 22 Class 5	ASTM	USA	Steel and Forging
A 217 Grade WC9	ASTM	USA	Steel and Casting
10028-2 1.7380	EN	European Union	Steel
17175 10 CrMo 9 10	DIN	Germany	Steel and Tubing
17243 1.7380	DIN	Germany	Steel and Bars

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.