GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASME SA-564 Type 632

Standard Specification for Hot-Rolled and Cold-Finished Age-Hardening Stainless Steel Bars and Shapes

Group - Ferrous Stainless Steel Alloys

Sub Group - ASME SA-564 Type 632 Hot-Rolled and Cold-Finished Age-Hardening Stainless Steel Bars and Shapes

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries
Grade Belongs to the Industry - Bars and Shapes

Chemical Composition		
Carbon	C %	0.090 max.
Manganese	Mn %	1.000 max.
Phosphorus	P %	0.040 max.
Sulphur	S %	0.030 max.
Silicon	Si %	1.000 max.
Chromium	Cr %	14.000 - 16.000
Nickel	Ni %	6.500 - 7.750
Aluminium	Al %	0.750 - 1.500
Molybdenum	Mo %	2.000 - 3.000
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Solution Annealing or Age-Hardening

Mechanical Properties	
Tensile Strength in Mpa	1380 min.
Yield Strength in Mpa	1210 min.
Elongation in %	7 min.
Reduction of Area in %	25 min.
Hardness in BHN	415 min.
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
S15700	UNS	USA	Steel
S15780	UNS	USA	Steel
SA-705 Type 632	ASME	USA	Steel and Forging
SA-693 632	ASME	USA	Plate, Sheet and Strip
35-574 Z 9 CNDA 15-07	AFNOR NF	France	Steel and Bars
1.4514	DIN	Germany	Steel
A 705 632	ASTM	USA	Steel and Forging

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.