GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASME SA-660 Grade WCA

Standard Specification for Centrifugally Cast Carbon Steel Pipe for High-Temperature Service

Group - Ferrous Mild Steel Alloys
Sub Group - ASME SA-660 Grade WCA Centrifugally Cast Carbon Steel Pipe for High-Temperature Service
Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries
Grade Belongs to the Industry - Steel and Pipe

Chemical Composition		
Carbon	C %	0.250 max.
Manganese	Mn %	0.700 max.
Phosphorus	P %	0.035 max.
Sulphur	S %	0.035 max.
Silicon	Si %	0.600 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Annealing or Normalizing or Normalizing & Tempering or Quenching & Tempering

Mechanical Properties	
Tensile Strength in Mpa	414 min.
Yield Strength in Mpa	207 min.
Elongation in %	24 min.
Reduction of Area in %	35 min.
Hardness in HB	-
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
J02504	UNS	USA	Steel
A 216 WCA	ASTM	USA	Casting
SA-216 WCA	ASME	USA	Casting
SA-216 WCB	ASME	USA	Casting
SA-216 WCC	ASME	USA	Casting
10132-2 1.0619	EN	European Union	Casting
10132-2 1.0619	DIN	Germany	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.