



GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASME SA-731 18 Cr-2Mo

Standard Specification for Seamless and Ferritic Stainless Steel Pipe Intended for High Temperature and General Corrosive Service

Group - Ferrous Stainless Steel Alloys

Sub Group - ASME SA-731 18 Cr-2Mo Seamless and Ferritic Stainless Steel Pipe Intended for High Temperature and General Corrosive Service

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.025 max.	Normalising or Annealing or Hardening + Tempering	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	17.500 - 19.500		
Molybdenum	Mo %	1.750 - 2.500		
Ti + Nb	Ti% + Nb%	0.800 max.	Mechanical Properties Tensile Strength in Mpa 415 min. Yield Strength in Mpa 275 min. Elongation in % 20 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
Nitrogen	N %	0.035 max.		
Ni+Cu	Ni% + Cu%	1.000 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
444	AS	Australia	Plate, Sheet and Strip
A176 S44400	ASTM	USA	Plate, Sheet and Strip
F.3123	UNE	Spain	Casting
S44400	UNS	USA	Plate, Sheet and Strip
X 2 CrMoTiNb 18-2	UNE	Spain	Plate, Sheet and Strip
444	SAE	USA	Plate, Sheet and Strip
A731 18Cr-2Mo	ASTM	USA	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS