



GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASME SA-789 UNS S39274

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - ASME SA-789 UNS S39274 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	Solution Annealing	
Silicon	Si %	0.800 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	24.000 - 26.000		
Nickel	Ni %	6.000 - 8.000		
Molybdenum	Mo %	2.500 - 3.500		
Nitrogen	N %	0.240 - 0.320		
Copper	Cu %	0.200 - 0.800		
Tungsten	W %	1.500 - 2.500	Mechanical Properties Tensile Strength in Mpa 800 min. Yield Strength in Mpa 550 min. Elongation in % 15 min. Reduction of Area in % 30 min. Hardness in HB 310 max. Impact in Joule -	
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A240 UNS S39274	ASTM	USA	Steel, Plate, Sheet and Strip
S39274	UNS	USA	Steel
A789 S39274	ASTM	USA	Steel and Tube
A790 S39274	ASTM	USA	Steel and Pipe
A815 S39274	ASTM	USA	Steel and Pipe
A959 S39274	ASTM	USA	Steel and Pipe
A988 S39274	ASTM	USA	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS