GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASME SA-965 Grade F347H

Standard Specification for Steel Forgings, Austenitic, for Pressure and High Temperature Parts

Group - Ferrous Stainless Steel Alloys
Sub Group - ASME SA-965 Grade F347H Steel Forgings, Austenitic, for Pressure and High Temperature Parts
Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries
Grade Belongs to the Industry - Forging

Chemical Composition		
Carbon	C %	0.040 - 0.100
Manganese	Mn %	2.000 max.
Phosphorus	P %	0.045 max.
Sulphur	S %	0.030 max.
Silicon	Si %	1.000 max.
Nickel	Ni %	9.000 - 12.000
Chromium	Cr %	17.000 - 19.000
Nb + Ta	Nb%+Ta%	0.008 - 1.100
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	485 min.
Yield Strength in Mpa	205 min.
Elongation in %	30 min.
Reduction of Area in %	45 min.
Hardness in HB	-
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
S34709	UNS	USA	Steel
J 405 347	SAE	USA	Steel
D 3698 STS 347	KS	Korea	Plate, Sheet and Strip
G 4319 SUS 347 HFB	JIS	Japan	Steel and Forging
G 3459 SUS 347 HTP	JIS	Japan	Steel and Pipe
A 403 WP 347H	ASTM	USA	Steel and Pipe
A 959 Type 347H	ASTM	USA	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.