



GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASME SA487 Grade 11A

Standard Specification for Low Alloy Steel and Martensitic Stainless Steel Castings

Group - Ferrous Mild Steel Alloys

Sub Group - ASME SA487 Grade 11A Low Alloy Steel and Martensitic Stainless Steel Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 - 0.200	Normalising or Annealing or Hardening + Tempering	
Silicon	Si %	0.600 max.		
Manganese	Mn %	0.500 - 0.800		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.035 max.		
Chromium	Cr %	0.500 - 0.800		
Nickel	Ni %	0.700 - 1.100		
Molybdenum	Mo %	0.450 - 0.650		
Vanadium	V %	0.030 max.		
Tungsten	W %	0.100 max.		
Copper	Cu %	0.500 max.	Mechanical Properties Tensile Strength in Mpa 484 - 655 Yield Strength in Mpa 275 min. Elongation in % 20 min. Reduction of Area in % 35 min. Hardness in BHN - Impact in Joule -	
Other	Ot %	0.500 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SA217 Grade WC4	ASME	USA	Casting
A487 Grade 11	ASTM	USA	Casting
J12082	UNS	USA	Casting
SA487 Grade 11B	ASME	USA	Casting
A217 Grade WC4	ASTM	USA	Casting
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS