



Material - ASTM A 1040 1026

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 1040 1026 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.220 - 0.280		
Manganese	Mn %	0.600 - 0.900	As Raw or Annealing or Normalizing or Hardening and Tempering	
Phosphorus	P %	0.030 max.		lizing or Hardoning and
Sulphur	S %	0.035 max.		· ·
Boron	В%	0.0005 - 0.003		
Copper	Cu %	0.200 min.		
Silicon	Si %	0.100 max.		
Iron	Fe %	Balance		
-	-		Mechanical Properties	
-	-	-	Tensile Strength in Mpa	415 min.
-	-	-	Yield Strength in Mpa	240 min
-	-	-	Elongation in %	5 min.
-	-	-	Reduction of Area in %	40 - 49
-	-	-	Hardness in HB	126 - 143
-	-	-	Impact in Joule	-

Cross Reference Table				
Material	Standard	Country Grade Belong to the Industry		
G10260	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing	
1026	SAE	USA	Steel	
1026	AISI	USA	Tubing	
A 29 1026	ASTM	USA	Steel and Bar	
A 510 1026	ASTM	USA	Wire Rod and Round Wire	
A 512 Grade 1026	ASTM	USA	Tubing	
A 513 Grade 1026	ASTM	USA	Tubing	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.