



Material - ASTM A 1040 1030

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 1040 1030 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel

Chemical Composition		Heat Treatment	
C %	0.280 - 0.340	As Raw or Annealing or Normalizing or Hardening and Tempering	
Mn %	0.600 - 0.900		
P %	0.030 max.		alizing or Hardoning and
S %	0.035 max.		· ·
В%	0.0005 - 0.003		irig
Cu %	0.200 max.		
Si %	0.100 max.		
Fe %	Balance		
-		Mechanical Properties	
-	-	Tensile Strength in Mpa	415 - 896
-	-	Yield Strength in Mpa	260 min.
-	-	Elongation in %	5 min.
-	-	Reduction of Area in %	35 - 42
-	-	Hardn <mark>ess in HB</mark>	137 - 149
-	-	Impact in Joule	36.9 - 52.3 J @ RT
	C % Mn % P % S % B % Cu % Si % Fe %	C % 0.280 - 0.340 Mn % 0.600 - 0.900 P % 0.030 max. S % 0.035 max. B % 0.0005 - 0.003 Cu % 0.200 max. Si % 0.100 max. Fe % Balance	C % 0.280 - 0.340 Mn % 0.600 - 0.900 P % 0.030 max. S % 0.035 max. B % 0.0005 - 0.003 Cu % 0.200 max. Si % 0.100 max. Fe % Balance - Tensile Strength in Mpa Yield Strength in Mpa Yield Strength in Mpa Elongation in % Reduction of Area in % Hardness in HB

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
G10300	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing	
1030	SAE	USA	Steel	
1030	AISI	USA	Tubing	
A 108 Grade 1030	ASTM	USA	Steel and Bar	
A 29 1030	ASTM	USA	Steel and Bar	
A 510 1030	ASTM	USA	Wire Rod and Round Wire	
A 512 Grade 1030	ASTM	USA	Tubing	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.