



## Material - ASTM A 1040 1037

**Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel**

**Group - Ferrous Mild Steel Alloys**

**Sub Group - ASTM A 1040 1037 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel**

**Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries**

**Grade Belongs to the Industry - Steel**

Chemical Composition			Heat Treatment	
Carbon	C %	0.320 - 0.380	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.700 - 1.000		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.035 max.		
Boron	B %	0.0005 - 0.003		
Silicon	Si %	0.100 max.		
Copper	Cu %	0.200 max.		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	510 - 570
-	-	-	Yield Strength in Mpa	280 min.
-	-	-	Elongation in %	12 min.
-	-	-	Reduction of Area in %	35 - 40
-	-	-	Hardness in HB	143 - 167
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G10370	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1037	SAE	USA	Steel
1037	AISI	USA	Steel and Bar
A 29 1037	ASTM	USA	Steel and Bar
A 510 1037	ASTM	USA	Wire Rod and Round Wire
A 576 10L37	ASTM	USA	Steel and Bar
A 830 1037	ASTM	USA	Plate

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.