



Material - ASTM A 1040 1060

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled Steel

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 1040 1060 Carbon Steel Compositions For Forging To Hot-Rolled Steel

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.550 - 0.650	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.600 - 0.900		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.035 max.		
Boron	B %	0.0005 - 0.003		
Copper	Cu %	0.200 min.		
Silicon	Si %	0.100 max.		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 620 - 680 Yield Strength in Mpa 370 min. Elongation in % 10 min. Reduction of Area in % 30 - 45 Hardness in HB 183 - 201 Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G10600	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1060	SAE	USA	Steel
1060	AISI	USA	Steel and Tubing
A 29 1060	ASTM	USA	Steel and Bar
A 510 1060	ASTM	USA	Wire Rod, Round Rod and Steel
A 513 Grade 1060	ASTM	USA	Steel and Tubing
A 576 10L60	ASTM	USA	Bar

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.