

## Material - ASTM A 108 Grade 1018

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

**Group - Ferrous Mild Steel Alloys** 

Sub Group - ASTM A 108 Grade 1018 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel and Bar

Chemical Composition		Heat Treatment	
C %	0.150 - 0.200		
Mn %	0.600 - 0.900	As Raw or Annealing or Normalizing or Hardening and Tempering	
P %	0.040 max.		
S %	0.050 max.		
Pb %	0.150 - 0.350		
Si %	0.100 max.		
Fe %	Balance		
-	-		
-	-	Mechanical Pr	operties
-	-	Tensile Strength in Mpa	380 - 690
-	-	Yield Strength in Mpa	220 min.
-	-	Elongation in %	13 min.
-	-	Reduction of Area in %	35 min.
-	-	Hardness in HB	241 max.
-	-	Impac <mark>t in Joule</mark>	-
	Mn % P % S % Pb % Si % Fe %	Mn % 0.600 - 0.900  P % 0.040 max.  S % 0.050 max.  Pb % 0.150 - 0.350  Si % 0.100 max.  Fe % Balance	Mn %         0.600 - 0.900           P %         0.040 max.           S %         0.050 max.           Pb %         0.150 - 0.350           Si %         0.100 max.           Fe %         Balance           -         -           Tensile Strength in Mpa           Yield Strength in Mpa           Yield Strength in Mpa           Elongation in %           Reduction of Area in %           Hardness in HB

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
G10180	UNS	USA	Bars, Wire Rods and Tubing	
1018	SAE	USA	Steel	
1018	AISI	USA	Tubing	
A 1040 1018	ASTM	USA	Steel	
A 29 1018	ASTM	USA	Steel and Bar	
A 311 1018 Class A	ASTM	USA	Steel and Bar	
A 510 1018	ASTM	USA	Wire Rod and Round Wire	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.