

Material - ASTM A 108 Grade 1040

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bar

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 108 Grade 1040 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bar Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Bar

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|---------------|--|-------------------------|
| Carbon | C % | 0.370 - 0.440 | | |
| Manganese | Mn % | 0.600 - 0.900 | As Raw or Annealing or Normalizing or Hardening and Tempering | |
| Phosphorus | P % | 0.040 max. | | dizing or Hardoning and |
| Sulphur | S % | 0.050 max. | | • |
| Lead | Pb % | 0.150 - 0.350 | | ıg |
| Silicon | Si % | 0.100 max. | | |
| Iron | Fe % | Balance | | |
| - | - | - | | |
| - | /- | - | Mechanical Properties | |
| - | - | - | Tensile Strength in Mpa | 418 min. |
| - | - | - | Yield Strength in Mpa | 290 min. |
| - | - | - | Elongation in % | 5 min. |
| - | - | - | Reduction of Area in % | 35 - 40 |
| - | - | - | Hardness in HB | 149 - 170 |
| - | - | - | Impa <mark>ct in Joule</mark> | - |
| - | - | | | 149 - 170 - |

| Cross Reference Table | | | | | |
|-----------------------|----------|--------------------------------------|---|--|--|
| Material | Standard | Country Grade Belong to the Industry | | | |
| G10400 | UNS | USA | Bars, Wire Rods, Plates, Strip, Sheets and Tubing | | |
| 1040 | SAE | USA | Steel | | |
| 1040 | AISI | USA | Tubing | | |
| A 1040 1040 | ASTM | USA | Steel | | |
| A 29 1040 | ASTM | USA | Steel | | |
| A 513 Grade 1040 | ASTM | USA | Tubing | | |
| A 510 1040 | ASTM | USA | Wire Rod and Round Wire | | |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.