

## Material - ASTM A 108 Grade 1141

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

**Group - Ferrous Mild Steel Alloys** 

Sub Group - ASTM A 108 Grade 1141 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel and Bar

Chemical Composition			Heat Treatment	
Carbon	C %	0.370 - 0.450		
Manganese	Mn %	1.350 - 1.650	As Raw or Annealing or Normalizing or Hardening and Tempering	
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.080 - 0.130		
Silicon	Si %	0.100 max.		
Lead	Pb %	0.150 - 0.350		
Iron	Fe %	Balance		
-	-	-		
-	-	-	Mechanical Pro	perties
-	-	-	Tensile Strength in Mpa	550 min.
-	-	-	Yield Strength in Mpa	360 min.
-	-	-	Elongation in %	10 min.
-	-	-	Reduction of Area in %	30 min.
-	-	-	Hardn <mark>ess in HB</mark>	187 - 321
-	-		Impac <mark>t in Joule</mark>	-

	Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry		
G11410	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing		
1141	SAE	USA	Steel		
1141	AISI	USA	Steel and Bar		
A 1040 1141	ASTM	USA	Steel		
A 29 1141	ASTM	USA	Steel and Bar		
A 311 1141 Class A	ASTM	USA	Steel and Bar		
A 311 1141 Class B	ASTM	USA	Steel and Bar		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.