

Material - ASTM A 108 Grade 1144

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 108 Grade 1144 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel and Bar

Chemical Composition			Heat Treatment	
Carbon	C %	0.400 - 0.480	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	1.350 - 1.650		
Phosphorus	Р%	0.040 max.		
Sulphur	S %	0.240 - 0.330		
Silicon	Si %	0.100 max.		
Lead	Pb %	0.150 - 0.350		
Iron	Fe %	Balance		
-	-	-		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	585 min.
-	-	-	Yield Strength in Mpa	370 min.
-	-	-	Elongation in %	5 min.
-	-	-	Reduction of Area in %	20 min.
-	-	-	Hardn <mark>ess in HB</mark>	197 - 321
-	-		Impac <mark>t in Joule</mark>	-

Cross Reference Table					
Material	Standard	Country	ountry Grade Belong to the Industry		
G11440	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing		
1144	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing		
1144	AISI	USA	Steel and Bar		
A 1040 1144	ASTM	USA	Steel		
A 29 1144	ASTM	USA	Steel and Bar		
A 311 1144 Class A	ASTM	USA	Steel and Bar		
A 311 1144 Class B	ASTM	USA	Steel and Bar		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.