

Material - ASTM A 108 Grade 1213

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 108 Grade 1213 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel and Bar

Chemical Composition			Heat Treatment	
Carbon	C %	0.130 max.		
Manganese	Mn %	0.700 - 1.000	As Raw or Annealing or Normalizing or Hardening and Tempering	
Phosphorus	Р%	0.070 - 0.120		
Sulphur	S %	0.240 - 0.330		
Lead	Pb %	0.150 - 0.350		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	7	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	390 - 540
-	-	-	Yield Strength in Mpa	230 min.
-	-	-	Elongation in %	10 min.
-	-	-	Reduction of Area in %	35 - 45
-	-	-	Hardn <mark>ess in HB</mark>	121 - 167
-	-		Impact in Joule	-
-				

Cross Reference Table				
Material	Standard	Country Grade Belong to the Industry		
G12130	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing	
1213	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing	
1213	AISI	USA	Steel and Bar	
A 1040 1213	ASTM	USA	Steel	
A 576 1213	ASTM	USA	Steel and Bar	
SA-29 1213	ASME	USA	Steel	
A 29 1213	ASTM	USA	Steel and Bar	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.