

## Material - ASTM A 167 S30600

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

**Group - Ferrous Stainless Steel Alloys** 

Sub Group - ASTM A167 S30600 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel, Plate, Sheet and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.018 max.	Solution Annealing	
Silicon	Si %	3.700 - 4.300		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.020 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	17.000 - 18.500		
Molybdenum	Mo %	0.200 max.		
Nickel	Ni %	14.000 - 15.500		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	538 min.
-	-	-	Yield Strength in Mpa	240 min.
-	-	-	Elongation in %	40 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-		Impact in Joule	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
A240 UNS S30600	ASTM	USA	Steel, Plate, Sheet and Strip	
A959 S30600	ASTM	USA	Steel	
A269 S30600	ASTM	USA	Steel and Tube	
A312 S30600	ASTM	USA	Steel and Pipe	
A358 S30600	ASTM	USA	Steel and Pipe	
A479 S30600	ASTM	USA	Steel and Bar	
A943 S30600	ASTM	USA	Steel and Pipe	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.