



GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASTM A 167 S33228

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A 167 S33228 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel, Sheet, Plate and Strip

Chemical Composition			Heat Treatment			
Carbon	C %	0.040 - 0.080	Solution Annealing			
Silicon	Si %	0.300 max.				
Manganese	Mn %	1.000 max.				
Phosphorus	P %	0.020 max.				
Sulphur	S %	0.015 max.				
Chromium	Cr %	26.000 - 28.000				
Nickel	Ni %	31.000 - 33.000				
Cerium	Ce %	0.050 - 0.100				
Niobium	Nb %	0.600 - 1.000				
Aluminium	Al %	0.025 max.				
Iron	Fe %	Balance	<th colspan="2">Mechanical Properties</th>		Mechanical Properties	
-	-	-	Tensile Strength in Mpa	504 min.		
-	-	-	Yield Strength in Mpa	186 min.		
-	-	-	Elongation in %	30 min.		
-	-	-	Reduction of Area in %	-		
-	-	-	Hardness in HB	217 max.		
-	-	-	Impact in Joule	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A240 UNS S33228	ASTM	USA	Steel, Plate, Sheet and Strip
S33228	UNS	USA	Steel
A213 S33228	ASTM	USA	Steel and Tube
A312 S33228	ASTM	USA	Steel and Pipe
A249 S33228	ASTM	USA	Steel and Tube
A479 S33228	ASTM	USA	Steel and Bar
A959 S33228	ASTM	USA	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS