



Material - ASTM A 167 S34565

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A 167 S34565 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel, Sheet, Plate and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	5.000 - 7.000		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.010 max.		
Chromium	Cr %	23.000 - 25.000		
Molybdenum	Mo %	4.000 - 5.000		
Nickel	Ni %	16.000 - 18.000		
Niobium	Nb %	0.100 max.		
Nitrogen	N %	0.400 - 0.600		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	793 min.
-	-	-	Yield Strength in Mpa	414 min.
-	-	-	Elongation in %	35 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	241 max.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A240 UNS S34565	ASTM	USA	Steel, Plate, Sheet and Strip
S34565	UNS	USA	Steel
A213 S34565	ASTM	USA	Steel and Tube
A249 S34565	ASTM	USA	Steel and Tube
A276 S34565	ASTM	USA	Steel, Bar and Shapes
A312 S34565	ASTM	USA	Steel and Pipe
A959 S34565	ASTM	USA	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.