

## Material - ASTM A 182 F 316H

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications

**Group - Ferrous Stainless Steel Alloys** 

Sub Group - ASTM A 182 F 316H Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel, Pipe and Forging

Chemical Composition			Heat Treatment	
Carbon	C %	0.040 - 0.100		
Silicon	Si %	1.000 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.045 max.	Solution Ann	ealing
Sulphur	S %	0.030 max.		
Chromium	Cr %	16.000 - 18.000		
Molybdenum	Mo %	2.000 - 3.000		
Nickel	Ni %	10.000 - 14.000		
Iron	Fe %	Balance	Mechanical Pr	operties
-	-	-	Tensile Strength in Mpa	485 min.
-	-	-	Yield Strength in Mpa	205 min.
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	50 min.
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

	Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry		
A240 UNS S31609	ASTM	USA	Steel, Plate, Sheet and Strip		
316H	SAE	USA	Steel		
STS 316 HTP	KS	Korea	Steel and Pipe		
SUS F316H	JIS	Japan	Steel and Forging		
316	AISI	USA	Steel, Sheet, Strip and Plate		
316	SAE	USA	Steel, Bar, Wire, Shape and Forging		
316	AMS	USA	Steel, Bar, Wire, Shape and Forging		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.