

Material - ASTM A 213 S33228

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A 213 S33228 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel and Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.040 - 0.080	Solution Annealing	
Silicon	Si %	0.300 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.020 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	26.000 - 28.000		
Nickel	Ni %	31.000 - 33.000		
Cerium	Ce %	0.050 - 0.100		-
Niobium	Nb %	0.600 - 1.000	Mechanical Properties	
Aluminium	Al %	0.025 max.	Tensile Strength in Mpa	500 min.
Iron	Fe %	Balance	Yield Strength in Mpa	185 min.
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardn <mark>ess in HB</mark>	192 max.
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
A240 UNS S33228	ASTM	USA	Steel, Plate, Sheet and Strip	
S33228	UNS	USA	Steel	
A167 S33228	ASTM	USA	Steel, Sheet, Plate and Strip	
A312 S33228	ASTM	USA	Steel and Pipe	
A249 S33228	ASTM	USA	Steel and Tube	
A479 S33228	ASTM	USA	Steel and Bar	
A959 S33228	ASTM	USA	Steel	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.