

Material - ASTM A 213 TP 309Cb

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A 213 TP 309Cb Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel and Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 max.		
Silicon	Si %	1.000 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.045 max.	Solution Annealing	
Sulphur	S %	0.030 max.		
Chromium	Cr %	22.000 - 24.000		
Nickel	Ni %	12.000 - 16.000		
Niobium	Nb %	1.100 max.		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	515 min.
-	-	-	Yield Strength in Mpa	205 min.
-	-	-	Elongation in %	35 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	192 max.
-	-	-	Impact in Joule	-

Cross Reference Table					
Material	Standard	Country Grade Belong to the Industry			
A240 UNS S30940	ASTM	USA	Steel, Plate, Sheet and Strip		
309Cb	SAE	USA	Steel		
A276 309Cb	ASTM	USA	Steel, Bar and Shapes		
A314 309Cb	ASTM	USA	Steel, Bar, Rods and Forging		
A358 309Cb	ASTM	USA	Steel and Pipe		
A479 309Cb	ASTM	USA	Steel and Bar		
A249 TP 309Cb	ASTM	USA Steel and Tube			

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.