

## Material - ASTM A 213 XM-15

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

**Group - Ferrous Stainless Steel Alloys** 

Sub Group - ASTM A 213 XM-15 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel and Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 max.		
Silicon	Si %	1.500 - 2.500		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.030 max.	Solution Annealing	
Sulphur	S %	0.030 max.		
Chromium	Cr %	17.000 - 19.000		
Nickel	Ni %	17.500 - 18.500		
Iron	Fe %	Balance		_
-	1	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	515 min.
-	-	-	Yield Strength in Mpa	205 min.
-	-	-	Elongation in %	35 min.
-	-		Reduction of Area in %	
-	-	-	Hardness in HB	192 max.
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country Grade Belong to the Industry		
A240 UNS S38100	ASTM	USA	Steel, Plate, Sheet and Strip	
S38100	UNS	USA	Steel	
A167 XM-15	ASTM	USA	Steel, Sheet, Plate and Strip	
A249 TPXM-15	ASTM	USA	Steel and Tube	
A269 TPXM-15	ASTM	USA	Steel and Tube	
A312 TPXM-15	ASTM	USA	Steel and Pipe	
A943 TPXM-15	ASTM	USA	Steel and Pipe	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.