

Material - ASTM A 268 S43940

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A 268 S43940 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel and Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.		
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.	Annealing or Hardening + Tempering	
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	17.500 - 18.500		
Titanium	Ti %	0.100 - 0.600		
Niobium	Nb %	0.300 max.		-
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	430 min.
-	-	-	Yield Strength in Mpa	205 min.
-	-	-	Elongation in %	11 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	180 max.
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
A240 UNS S43932	ASTM	USA	Steel, Plate, Sheet and Strip		
S43932	UNS	USA	Steel		
A959 S43932	ASTM	USA	Steel		
S43940	UNS	USA	Steel		
A240 UNS S43940	ASTM	USA	Steel, Sheet, Plate and Strip		
A959 S43940	ASTM	USA	Steel		
-	-	-	-		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.