



GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASTM A 276 S30815

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A 276 S30815 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel, Bar and Shapes

Chemical Composition			Heat Treatment	
Carbon	C %	0.050 - 0.100	Solution Annealing	
Silicon	Si %	1.400 - 2.000		
Manganese	Mn %	0.800 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	20.000 - 22.000		
Nickel	Ni %	10.000 - 12.000		
Cerium	Ce %	0.030 - 0.080		
Nitrogen	N %	0.140 - 0.200		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 600 min. Yield Strength in Mpa 310 min. Elongation in % 40 min. Reduction of Area in % 50 min. Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A240 UNS S30815	ASTM	USA	Steel, Plate, Sheet and Strip
S30815	UNS	USA	Steel, Plate, Sheet and Strip
S30815	AS	Australia	Steel, Plate, Sheet and Strip
A167 S30815	ASTM	USA	Steel, Plate, Sheet and Strip
A249 S30815	ASTM	USA	Steel and Tube
A409 S30815	ASTM	USA	Steel and Pipe
A959 S30815	ASTM	USA	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS