

## Material - ASTM A 276 S32304

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications

**Group - Ferrous Stainless Steel Alloys** 

Sub Group - ASTM A 276 S32304 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel, Bar and Shapes

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	2.500 max.		
Phosphorus	Р%	0.040 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	21.500 - 24.500		
Nickel	Ni %	3.000 - 5.500		
Molybdenum	Mo %	0.050 - 0.600		
Nitrogen	N %	0.050 - 0.200	Mechanical Properties	
Copper	Cu %	0.050 - 0.600	Tensile Strength in Mpa	600 min.
Iron	Fe %	Balance	Yield Strength in Mpa	400 min.
-	-	-	Elongation in %	25 min.
	-	-	Reduction of Area in %	-
-	-	-	Hardn <mark>ess in HB</mark>	290 max.
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country Grade Belong to the Industry		
A240 UNS S32304	ASTM	USA	Steel, Plate, Sheet and Strip	
\$32304	UNS	USA	Steel	
A789 S32304	ASTM	USA	Steel and Tube	
A790 S32304	ASTM	USA	Steel and Tube	
A928 S32304	ASTM	USA	Steel and Pipe	
S32304	AS	Australia	Steel, Sheet, Plate and Strip	
SA-276 S32304	ASME	USA	Steel, Bar and Shapes	

## Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

## ONE STOP SOLUTION FOR METAL PARTS