

Material - ASTM A 276 S32654

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A 276 S32654 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel, Bar and Shapes

Chemical Composition			Heat Treatment	
Carbon	C %	0.020 max.		
Silicon	Si %	0.500 max.		
Manganese	Mn %	2.000 - 4.000	Solution Annealing	
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.005 max.		
Chromium	Cr %	24.000 - 25.000		
Molybdenum	Mo %	7.000 - 8.000		
Nickel	Ni %	21.000 - 23.000		_
Copper	Cu %	0.300 - 0.600	Mechanical Properties	
Nitrogen	N %	0.450 - 0.550	Tensile Strength in Mpa	750 min.
Iron	Fe %	Balance	Yield Strength in Mpa	430 min.
-	-	-	Elongation in %	40 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	250 max.
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
A240 UNS S32654	ASTM	USA	Steel, Plate, Sheet and Strip		
S32654	UNS	USA	Steel		
A167 S32654	ASTM	USA	Steel, Sheet, Plate and Strip		
A249 S32654	ASTM	USA	Steel and Tube		
A269 S32654	ASTM	USA	Steel and Tube		
A312 S32654	ASTM	USA	Steel and Pipe		
A959 S32654	ASTM	USA	Steel		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.