



**GRAVITY CAST PVT. LTD.**  
**GRAVITY GROUP OF COMPANIES**

## Material - ASTM A 29 M1023

**Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar**

**Group - Ferrous Mild Steel Alloys**

**Sub Group - ASTM A 29 M1023 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar**

**Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries**

**Grade Belongs to the Industry - Steel and Bar**

Chemical Composition			Heat Treatment	
Carbon	C %	0.190 - 0.270	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.250 - 0.600		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.050 max.		
Aluminium	Al %	0.020 max.		
Niobium	Nb %	0.025 max.		
Vanadium	V %	0.050 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	370 - 430
			Yield Strength in Mpa	210 min
			Elongation in %	15 min.
			Reduction of Area in %	40 - 50
			Hardness in HB	111 - 121
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G10230	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1023	SAE	USA	Steel
1023	AISI	USA	Steel and Bar
A 1040 1023	ASTM	USA	Steel
A 29 1023	ASTM	USA	Steel and Bar
A 510 1023	ASTM	USA	Wire Rod and Round Wire
A 513 Grade 1023	ASTM	USA	Tubing

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

**ONE STOP SOLUTION FOR METAL PARTS**