

Material - ASTM A 29 1132

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 29 1132 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

Chemical Composition Heat Treatment 0.270 - 0.340 Carbon C % Manganese Mn % 1.350 - 1.650 **Phosphorus** Ρ% 0.040 max. As Raw or Annealing or Normalizing or Hardening and Sulphur 0.080 - 0.130 S % Tempering Silicon Si % 0.100 max. Aluminium AI % 0.020 max. Niobium Nb % 0.015 Max. V % Vanadium 0.020 max. **Mechanical Properties** Iron Fe % Balance Tensile Strength in Mpa _ _ 550 - 760 Yield Strength in Mpa 310 - 620 _ _ _ 12 - 23 Elongation in % _ Reduction of Area in % 35 - 40 _ _ Hardness in HB 164 - 217 _ _ _ Impact in Joule

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel and Bar

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G11320	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1132	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1132	AISI	USA	Steel and Bar
A 1040 1132	ASTM	USA	Steel
A 510 1132	ASTM	USA	Wire Rod, Round Wire and Steel
A 519 1132	ASTM	USA	Steel and Tubing
A 576 11L32	ASTM	USA	Steel and Bar

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS