



Material - ASTM A 29 1141

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 29 1141 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel and Bar

Chemical Composition			Heat Treatment	
Carbon	C %	0.370 - 0.450	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	1.350 - 1.650		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.080 - 0.130		
Silicon	Si %	0.100 max.		
Aluminium	Al %	0.020 max.		
Niobium	Nb %	0.015 max.		
Vanadium	V %	0.020 max.		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	550 min.
-	-	-	Yield Strength in Mpa	360 min.
-	-	-	Elongation in %	10 min.
-	-	-	Reduction of Area in %	30 min.
-	-	-	Hardness in HB	187 - 321
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G11410	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1141	SAE	USA	Steel
1141	AISI	USA	Steel and Bar
A 1040 1141	ASTM	USA	Steel
A 108 Grade 1141	ASTM	USA	Steel and Bar
A 311 1141 Class A	ASTM	USA	Steel and Bar
A 311 1141 Class B	ASTM	USA	Steel and Bar

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.