



Material - ASTM A 29 1522

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled Steel and Bar

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 29 1522 Carbon Steel Compositions For Forging To Hot-Rolled Steel and Bar

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel and Bar

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|----------------|---|--|
| Carbon | C % | 0.180 - 0.240 | As Raw or Annealing or Normalizing or Hardening and Tempering | |
| Manganese | Mn % | 1.100 - 1.140 | | |
| Phosphorus | P % | 0.040 max. | | |
| Sulphur | S % | 0.050 max. | | |
| Boron | B % | 0.0005 - 0.003 | | |
| Aluminium | Al % | 0.020 max. | | |
| Copper | Cu % | 0.200 max. | | |
| Niobium | Nb % | 0.025 max. | | |
| Silicon | Si % | 0.100 max. | | |
| Vanadium | V % | 0.050 max. | | |
| Iron | Fe % | Balance | Mechanical Properties Tensile Strength in Mpa 410 min. Yield Strength in Mpa 340 min. Elongation in % 22 min. Reduction of Area in % - Hardness in BHN - Impact in Joule - | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |

| Cross Reference Table | | | |
|-----------------------|----------|---------|---|
| Material | Standard | Country | Grade Belong to the Industry |
| G15220 | UNS | USA | Bars, Wire Rods, Plates, Strip, Sheets and Tubing |
| 1522 | SAE | USA | Bars, Wire Rod and Tubing |
| 1522 | AISI | USA | Steel and Bar |
| A 510 1522 | ASTM | USA | Wire Rods, Round Wire and Steel |
| A 576 15L22 | ASTM | USA | Steel and Bar |
| - | - | - | - |
| - | - | - | - |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.