

Material - ASTM A 29 M1015

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 29 M1015 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel and Bar

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|---------------|--|--------------------------|
| Carbon | C % | 0.120 - 0.190 | | |
| Manganese | Mn % | 0.250 - 0.600 | As Raw or Annealing or Normalizing or Hardening and Tempering | |
| Phosphorus | P % | 0.040 max. | | alizing or Hardoning and |
| Sulphur | S % | 0.050 max. | | |
| Aluminium | Al % | 0.020 max. | | |
| Niobium | Nb % | 0.025 max. | | |
| Vanadium | V % | 0.050 max. | | |
| Iron | Fe % | Balance | | |
| - | - | - | Mechanical Properties | |
| - | - | - | Tensile Strength in Mpa | 310 - 655 |
| - | - | - | Yield Strength in Mpa | 190 min. |
| - | - | - | Elongation in % | 5 min. |
| - | - | - | Reduction of Area in % | 40 - 50 |
| - | - | - | Hardness in HB | 241 max. |
| - | - | - | Impac <mark>t in Joule</mark> | - |

| Cross Reference Table | | | | |
|-----------------------|----------|--------------------------------------|---|--|
| Material | Standard | Country Grade Belong to the Industry | | |
| G10150 | UNS | USA | Bars, Wire Rods, Plates, Strip, Sheets and Tubing | |
| 1015 | SAE | USA | Steel, Bar, Forging and Tubing | |
| 1015 | AISI | USA | Tubing | |
| A 1040 1015 | ASTM | USA | Steel | |
| A 108 Grade 1015 | ASTM | USA | Steel and Bar | |
| A 29 1015 | ASTM | USA | Steel and Bar | |
| A 512 Grade 1015 | ASTM | USA | Tubing | |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.