

## Material - ASTM A 311 1050 Class B

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

**Group - Ferrous Mild Steel Alloys** 

Sub Group - ASTM A 311 1050 Class B Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel and Bar

Chemical Composition			Heat Treatment	
Carbon	C %	0.480 - 0.550		
Manganese	Mn %	0.600 - 0.900		
Phosphorus	P %	0.040 max.	As Raw or Annealing or Normalizing or Hardening and Tempering	
Sulphur	S %	0.050 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	7	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	795 min.
-	-	-	Yield Strength in Mpa	690 min.
-	-	-	Elongation in %	7 min.
-	-	-	Reduction of Area in %	20 min.
-	-	-	Hardness in HB	-
-	-		Impact in Joule	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
G10500	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing		
1050	SAE	USA	Steel, Sheet, Strip and Plate		
1050	AISI	USA	Steel, Sheet, Strip and Plate		
A 311 1050 Class A	ASTM	USA	Steel and Bar		
A 513 Grade 1050	ASTM	USA	Steel and Tubing		
A 684 Grade 1050	ASTM	USA	Steel and Strip		
A 108 Grade 1050	ASTM	USA	Steel and Bar		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.