

Material - ASTM A 311 1541 Class B

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bar and Steel

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 311 1541 Class B Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bar and Steel

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Bar and Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.360 - 0.440		
Manganese	Mn %	1.350 - 1.650	As Raw or Annealing or Normalizing or Hardening and Tempering	
Phosphorus	P %	0.040 max.		alizing or Hardoning and
Sulphur	S %	0.050 max.		-
Iron	Fe %	Balance		ııg
-	-	-		
-	-	-		
-	-	-		
-	-	-	Mechanical Pr	operties
-	-	-	Tensile Strength in Mpa	795 min.
-	-	-	Yield Strength in Mpa	690 min.
-	-	-	Elongation in %	7 min.
-	-	-	Reduction of Area in %	20 min.
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
G15410	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing		
1541	SAE	USA	Bars, Plates, Strip, Sheets, Tubing and Forging		
1541	AISI	USA	Bar and Steel		
A 29 1541	ASTM	USA	Bar and Steel		
A 311 1541 Class A	ASTM	USA	Bar and Steel		
A 830 G15410	ASTM	USA	Plate and Steel		
A 510 1541	ASTM	USA	Wire Rod, Round Wire and Steel		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.