

Material - ASTM A 312 S30415

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A 312 S30415 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel and Pipe

Chemical Composition			Heat Treatment	
Carbon	C %	0.040 - 0.060	Solution Annealing	
Silicon	Si %	1.000 - 2.000		
Manganese	Mn %	0.800 max.		
Phosphorus	P %	0.045 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	18.000 - 19.000		
Nickel	Ni %	9.000 - 10.000		
Cerium	Ce %	0.030 - 0.080		
Nitrogen	N %	0.120 - 0.180	Mechanical Properties	
Iron	Fe %	Balance	Tensile Strength in Mpa	600 min.
-	-	-	Yield Strength in Mpa	290 min.
-	-	-	Elongation in %	25 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
A240 UNS S30415	ASTM	USA	Steel, Plate, Sheet and Strip		
S30415	UNS	USA	Steel		
A167 S30415	ASTM	USA	Steel, Sheet, Plate and Strip		
A249 S30415	ASTM	USA	Steel and Tube		
A358 S30415	ASTM	USA	Steel and Pipe		
A959 S30415	ASTM	USA	Steel		
SA-312 UNS S30415	ASME	USA	Steel and Pipe		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.