



Material - ASTM A 314 S42000

Standard Specification for Steel Billets and Bars for Forging for General Engineering Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A 314 S42000 Steel Billets and Bars for Forging for General Engineering Purposes Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Billets and Bars for Forging

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|-----------------|---|------------------------|
| Carbon | C % | 0.150 max. | | |
| Silicon | Si % | 1.000 max. | As Raw or Annealing or Normalizing or Hardening ar Tempering | |
| Manganese | Mn % | 1.000 max. | | izing or Hordoning and |
| Phosphorus | P % | 0.040 max. | | - |
| Sulphur | S % | 0.030 max. | | Б |
| Chromium | Cr % | 12.000 - 14.000 | | |
| Iron | Fe % | Balance | | |
| - | - | - | | |
| - | /- | - | Mechanical Properties | |
| - | - | - | Tensile Strength in Mpa | 690 max. |
| - | - | - | Yield Strength in Mpa | - |
| - | - | - | Elongation in % | 15 min. |
| - | - | - | Reduction of Area in % | - |
| - | - | - | Hardness in BHN | 217 max. |
| - | - | - | Impact in Joule | - |

| Cross Reference Table | | | | |
|-----------------------|----------|---------|------------------------------|--|
| Material | Standard | Country | Grade Belong to the Industry | |
| 420C28 | BS | British | Casting | |
| 420C29 | BS | British | Casting | |
| 420 | SAE | USA | Sheet, Strip and Plate | |
| 420 | AISI | USA | Forging | |
| A 176 S42000 | ASTM | USA | Steel Plate, Sheet and Strip | |
| A 176 Type 420 | ASTM | USA | Steel Plate, Sheet and Strip | |
| A 314 420 | ASTM | USA | Billets and Bars for Forging | |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.