

Material - ASTM A 358 309Cb

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A 358 309Cb Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel and Pipe

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|-----------------|-------------------------|----------|
| Carbon | C % | 0.080 max. | | |
| Silicon | Si % | 1.000 max. | | |
| Manganese | Mn % | 2.000 max. | | |
| Phosphorus | P % | 0.045 max. | Solution Annealing | |
| Sulphur | S % | 0.030 max. | | |
| Chromium | Cr % | 22.000 - 24.000 | | |
| Nickel | Ni % | 12.000 - 16.000 | | |
| Niobium | Nb % | 1.100 max. | | |
| Iron | Fe % | Balance | Mechanical Properties | |
| - | - | - | Tensile Strength in Mpa | 515 min. |
| - | - | - | Yield Strength in Mpa | 205 min. |
| - | - | - | Elongation in % | 30 min. |
| - | - | - | Reduction of Area in % | 40 min. |
| - | - | - | Hardness in BHN | - |
| - | - | - | Impact in Joule | - |

| Cross Reference Table | | | | |
|-----------------------|----------|--------------------------------------|-------------------------------|--|
| Material | Standard | Country Grade Belong to the Industry | | |
| A240 UNS S30940 | ASTM | USA | Steel, Plate, Sheet and Strip | |
| 309Cb | SAE | USA | Steel | |
| A276 309Cb | ASTM | USA | Steel, Bar and Shapes | |
| A314 309Cb | ASTM | USA | Steel, Bar, Rods and Forging | |
| A479 309Cb | ASTM | USA | Steel and Bar | |
| A213 TP309Cb | ASTM | USA | Steel and Tube | |
| A249 TP 309Cb | ASTM | USA Steel and Tube | | |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.