



Material - ASTM A 368 Type 316Cb

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A 368 Type 316Cb Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel and Wire

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 max.	Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.045 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	16.000 - 18.000		
Molybdenum	Mo %	2.000 - 3.000		
Nickel	Ni %	10.000 - 14.000	Mechanical Properties	
Nb + Ta	Nb% + Ta%	1.100 max.	Tensile Strength in Mpa	515 min.
Nitrogen	N %	0.100 max.	Yield Strength in Mpa	205 min.
Iron	Fe %	Balance	Elongation in %	40 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	217 max.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A240 UNS S31640	ASTM	USA	Steel, Plate, Sheet and Strip
316Cb	SAE	USA	Steel
A276 316Cb	ASTM	USA	Steel, Bar and Shapes
A314 316Cb	ASTM	USA	Steel, Bar, Rolling and Forging
A479 316Cb	ASTM	USA	Steel and Bar
A167 Type 316Cb	ASTM	USA	Steel, Sheet, Strip and Plate
A959 Type 316Cb	ASTM	USA	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.