

Material - ASTM A 403 WP S31725

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - ASTM A 403 WP S31725 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel and Pipe

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.		
Silicon	Si %	1.000 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.045 max.	Solution Annealing	
Sulphur	S %	0.030 max.		
Chromium	Cr %	18.000 - 20.000		
Molybdenum	Mo %	4.000 - 5.000		
Nickel	Ni %	13.500 - 17.500		
Nitrogen	N %	0.200 max.	Mechanical Properties	
Iron	Fe %	Balance	Tensile Strength in Mpa	750 min.
-	-	-	Yield Strength in Mpa	420 min.
-	-	-	Elongation in %	20 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
A240 UNS S31725	ASTM	USA	Steel, Plate, Sheet and Strip	
A358 S31725	ASTM	USA	Steel	
A943 S31725	ASTM	USA	Steel and Pipe	
SA-312 UNS S31725	ASME	USA	Steel and Pipe	
SA-376	ASME	USA	Steel and Pipe	
SA-409 UNS S31725	ASME	USA	Steel and Pipe	
A240 S31726	ASTM	USA Steel		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.